C&Lube Co., Ltd. since 1995
tel.82-52-239-5189 fax.82-52-239-5105

Special Lubricants
Custom Made Oils & Greases

182, Hwasan-ro, Onsan-up, UlJu-kun, Ulsan, KOREA, 45009
www.cnlube.co.kr, e-mail : adm@cnlube.co.kr

Certification of Analysis

Customer **INDIVIDUAL ENTREPRENUER** **D a t e** **14-Jul-22**

Product **EAGLE PAO 100 Synthetic 0W20 API SP C3** **Lot. No.** **22070824**

Test Item		Test Method	Spec.	Results
Appearance		Visual	Clear & Bright	Clear & Bright
Density(15℃), kg/㎥		ASTM D 287	Report	843.6
Kinematic Viscosity(100℃), ㎟/s		ASTM D 445	5.6 ~ 9.3	7.895
Viscosity Index		ASTM D 2270	85 min.	176
Apparent Viscosity (-35℃), Pa.S		ASTM D 5293	6.2 max.	4.40
Flash Point, ℃		ASTM D 92	180 min.	228
Pour Point, ℃		ASTM D 97	-36 max.	-51
Oxidation Stability (165.5℃, 24hr)	Viscosity Change Ratio	JIS K 2514	1.5 max.	0.98
	TAN Change ,㎎KOH/g		1.6 max.	0.30
	Lacquer		Thin	Nil

This data is for your reference and it can't be used for any legal purpose.

Research & Development Center

Manager J. H. Lee